

Glass Filled Nylon 12



Material description

Glass filled variant of Nylon 12 provides greater rigidity, perfect when prototyping rigid parts intended for production in advanced engineering thermoplastics, and is the right choice for functional testing. Form, fit and functional testing can now be completed without sacrifice. The filler is glass bead and not fibre; part predominantly increases in stiffness but not strength.

Material specification

Colour	White
Density of laser sintered part	1.23 to 1.28g/cm ³
Tensile modulus	3200 ± 200MPa
Tensile strength	48 ± 3MPa
Elongation at break	6 ± 3%
Flexural modulus	2100 ± 150 MPa
Melting point	172 to 180°C
Vicat softening temperature B/50	166°C
Vicat softening temperature A/50	179°C
Coefficient of thermal expansion	1.68 x 10 ⁻⁴ /K

All information in this data sheet is based on appropriate testing further details of which are available on request and is stated to the best of our knowledge and belief at the time of publication. It is presented apart from contractual obligations and does not constitute any guarantee or warranty express or implied of properties or of process or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. The data is subject to change without notice as part of our continuous development and improvement processes.

The content of this material data sheet may be subject to copyright restrictions. Quoted results are compiled from 3T AMP test data, EOS GmbH source data, and may contain data values from other material specific sources.