



Material description

Nylon 12 parts have good long term stability, offering resistance to most chemicals. Complexity is irrelevant. Delivers the impact strength and durability required for functional testing. Tensile and flexural strength combine to make tough prototypes, with the flex associated with many production thermoplastics.

Material specification

Colour	White
Density of laser sintered part	0.9 to 0.95g/cm ³
Tensile modulus	1700 ± 150MPa
Tensile strength	45 ± 3MPa
Elongation at break	20 ± 5%
Flexural modulus	1240 ± 130 MPa
Melting point	172 to 180°C
Vicat softening temperature B/50	163°C
Vicat softening temperature A/50	181°C
Coefficient of thermal expansion	1.09 x 10 ⁻⁴ /K

All information in this data sheet is based on appropriate testing further details of which are available on request and is stated to the best of our knowledge and belief at the time of publication. It is presented apart from contractual obligations and does not constitute any guarantee or warranty express or implied of properties or of process or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. The data is subject to change without notice as part of our continuous development and improvement processes.

The content of this material data sheet may be subject to copyright restrictions. Quoted results are compiled from 3T AMP test data, EOS GmbH source data, and may contain data values from other material specific sources.